

**PRODUCT INFORMATION**

|                       |                       |                                                                                    |                       |
|-----------------------|-----------------------|------------------------------------------------------------------------------------|-----------------------|
| Norm                  | EN ISO 26986          |                                                                                    |                       |
| Usage classification  | ISO 10874 (EN 685)    |  | 22 Domestic general   |
| Total thickness       | EN ISO 24346 (EN 428) |  | 2,50 mm               |
| Wear layer            | EN ISO 24340 (EN 429) |  | 0,20 mm               |
| Weight                | EN ISO 23997 (EN 430) |  | 1330 g/m <sup>2</sup> |
| Available roll widths | EN ISO 24341 (EN 426) |  | 2 - 3 - 4 m*          |
| Standard roll length  | EN ISO 24341 (EN 426) |  | +/- 25 m              |

**TECHNICAL INFORMATION**

|                                      |                                     |                                                                                      |                                         |
|--------------------------------------|-------------------------------------|--------------------------------------------------------------------------------------|-----------------------------------------|
| Abrasion group                       | EN 660-2                            |    | T                                       |
| Dimensional stability                | EN ISO 23999 (EN 434)               |    | ≤ 0,40 %                                |
| Curling                              | EN ISO 23999                        |                                                                                      | ≤ 8 mm                                  |
| Light stability                      | EN ISO 105 B02                      |    | ≥ 6                                     |
| Residual indentation                 | EN ISO 24343-1 (EN 433)             |    | ≤ 0,35 mm      required by the standard |
| Impact sound improvement             | EN ISO 717/2                        |    | Δ Lw 15 dB                              |
| Dynamic coefficient of friction      | EN 13893                            |   | > 0,60                                  |
| Slip resistance (ramp test with oil) | EN 16165:2021 – Annex B (DIN 51130) |  | R11                                     |
| Reaction to fire                     | EN 13501-1                          |  | Bfl-s1                                  |
| Underfloor heating                   | EN 12667                            |  | Suitable                                |
| Thermal resistance                   | ISO 8302                            |  | 0,0170 m <sup>2</sup> .K/W              |
| Thermal conductivity                 | ISO 10456                           |  | 0,147 W/(m.K)                           |
| Chemical resistance                  | ISO 26987 (EN 423)                  |  | Resistant                               |
| Static electrical propensity         | EN 1815                             |  | < 2 kV      on concrete                 |
| Top coating                          |                                     |  | Antislip PU                             |
| TVOC after 28 days                   | ISO 16000 (EN 16516)                |                                                                                      | <1000 µg/m <sup>3</sup>                 |
| Cold welding                         | Werner Müller                       |                                                                                      | Type A                                  |

\* check availability per individual reference

Please note that the data given could be imprecise and liable to modifications of a technical nature at any time. The information in these documents is valid from 19/6/2025 and Beauflor reserves the right to make changes at any moment, and without prior notice. Our technology is constantly evolving, so before carrying out any projects we encourage you to contact us to maintain our highest level of standards.

version 19/6/2025



**UK  
CA**

